

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
7 April 2005 (07.04.2005)

PCT

(10) International Publication Number  
WO 2005/031880 A1

(51) International Patent Classification<sup>7</sup>: H01L 31/0232,  
31/103

(21) International Application Number:  
PCT/US2004/031032

(22) International Filing Date:  
20 September 2004 (20.09.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
10/672,452 26 September 2003 (26.09.2003) US

(71) Applicant (for all designated States except US): SEMI-  
COA SEMICONDUCTORS [US/US]: 333 McCormick  
Avenue, Costa Mesa, CA 92626 (US).

(72) Inventors; and  
(75) Inventors/Applicants (for US only): GOUSHCHA,

Alexander, O. [UA/US]; 7418 Whitegate Avenue, River-  
side, CA 92506 (US). HICKS, Chris [US/US]; 2340  
Santa Ana Avenue #B3, Costa Mesa, CA 92627 (US).  
METZLER, Richard, A. [US/US]; 28232 Driva, Mission  
Viejo, CA 92692 (US).


(74) Agents: BLAKELY, Roger, W., Jr. et al.; Blakely,  
Sokoloff, Taylor & Zafman, 7th Floor, 12400 Wilshire  
Boulevard, Los Angeles, CA 90025-1026 (US).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GH, GM, GR, HU, IL, IN, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MY, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM,  
ZW.

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,

[Continued on next page]

(54) Title: FAST SILICON PHOTODIODES WITH HIGH BACK SURFACE REFLECTANCE IN A WAVELENGTH RANGE CLOSE TO THE BANDGAP



(57) Abstract: Fast silicon photodiodes with high back surface reflectance in a wavelength range close to the bandgap, and methods of fabrication of such photodiodes. The photodiodes have a patterned oxide or nitride layer on the back surface covered by a metal layer that makes electrical contact with the substrate in a pattern complementary to the pattern of the oxide or nitride layer. This provided high reflectivity over a large percentage of the back surface, while at the same time providing excellent electrical contact to the back surface.



ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BH, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,  
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

**Published:**

--- with international search report

**FAST SILICON PHOTODIODES  
WITH HIGH BACK SURFACE REFLECTANCE IN A WAVELENGTH RANGE  
CLOSE TO THE BANDGAP**

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to semiconductor photodiodes, in particular to silicon photodiodes with highly reflective back surfaces as well as to methods of fabricating such structures.

2. Prior Art

The performance of silicon photodiodes within the spectral range close to the bandgap ( $\sim 1124$  nm at  $23^\circ\text{C}$ ) depends on the quality of the back surface, as the light penetration depth at these wavelengths is large enough to span the entire thickness of the die. The light reflectance from the back surface of the die should be maximized to improve the responsivity and quantum efficiency of the photodiode.

As shown in Figure 1, prior art silicon photodiode structures use a sputtered metal layer or plating 1 (usually Au or Al) on the wafer back side over an n+ or p+ layer 2, followed by sintering at  $\sim 400^\circ\text{C}$  to provide a reliable back side electrical contact. Figure 1 also schematically shows the photodiode crystal bulk 3 and front side active area diffusion 4. As is well known, such structures are characterized by poor back surface reflectance, which becomes important for the wavelength range of  $\lambda \geq 950$  nm, since at these wavelengths the absorption length is comparable to the

die thickness. Note that the thickness of a conventional silicon photodiode die is within the range 200 to 500  $\mu\text{m}$ . Such thicknesses are usually required to absorb as much incident near infrared light as possible, thereby maximizing the photodiode responsivity at  $\lambda \geq 950 \text{ nm}$ .

To increase the quantum efficiency of silicon photodiodes in the near infrared spectral range, the back surface reflectance should be improved, and corresponding methods using isolation layers are well known from solar cell physics and technology. However, these methods are not readily used in silicon photodiode design. In addition, a dielectric isolation layer 5 with the thickness  $h$  between the back side metal and silicon may deteriorate significantly electrical properties of the back side contact, thereby forcing additional measures to improve the photodiodes' parameters such as responsivity, frequency bandwidth, rise time, etc. See Figure 2.

#### BRIEF DESCRIPTION OF THE DRAWINGS

The main ideas of the invention are demonstrated by the accompanying drawings.

Figure 1 is a simplified schematic cross section of a typical, conventional structure for a front illuminated photodiode with a metal layer sputtered or plated on the die back side.

Figure 2 is a simplified schematic cross section of a front illuminated photodiode with the dielectric isolation layer on the back side.

Figure 3 is a simplified schematic cross section of a photodiode structure having a back side mirror in accordance with the present invention.

Figure 4 shows schematically one arrangement of electrical contacts on the die back side.

Figure 5 is a schematic cross section of a completed photodiode in accordance with the present invention.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

As previously discussed, improving the back surface reflectance of photodiodes often causes deterioration of the photodiode performance with respect to such properties as frequency bandwidth and rise time. The present invention uses designs having an additional photomask on the wafer back side. This design corrects the above shortcomings, and provides for superior responsivity and temporal characteristics of silicon photodiodes within the spectral range close to the bandgap.

Now referring to Figure 3, a simplified cross section of a local region illustrating the back side detail of a photodiode in accordance with the present invention may be seen. The structure may be fabricated using either *n*-type or *p*-type bulk silicon substrate 3. For brevity, the region 4 of opposite conductivity type on the top surface of the substrate, the anode in the case of *p*-on-*n* structure or the cathode in the case of *n*-on-*p* structure will be referred to as "the first electrode", and the cathode in the case of *p*-on-*n* structure and the anode in the case of *n*-on-*p* structure, will be referred to as "the second electrode".

The structure is obtained using an additional photomask/etch process on the back side of the photodiodes, resulting in the so-called "back dielectric mirror" with a periodic contact structure between metal layer 1 and n+ or p+ layer 2 (a layer of the same conductivity type as the substrate 3, though of a higher conductivity than the substrate), like that shown in Figure 3. The thickness h of the dielectric layer (which, by way of example, may be an oxide or nitride layer) should preferably be approximately 1000 Å. In the exemplary structure of Figure 3, the extended regions of high reflectance of the back surface are separated from each other by the narrow strips of back side contact metal 1, which serves as the second electrode. The width b of the contact opening strip should be  $\geq 5 \mu\text{m}$  to provide a secure back side contact. The quality of the back side contact is important to get efficient and rapid collection of the non-equilibrium carriers. At the same time, the width of the contact opening should be kept as narrow as possible because the back side reflection from the contact area is considerably lower than the reflectance from the dielectric mirror. The ratio a/b - see Figure 3 - should be chosen taking into account requirements on the responsivity uniformity across the photodiode active area. For example, if the responsivity should be uniform with an accuracy of 5% when scanning the active area with the 1 mm diameter beam, then the total area  $S_{\text{cont}}$  of metal contacts enclosed inside the 1 mm diameter circle in any place across the back surface of the die should not exceed the value (see Figure 4 as an example):

$$S_{\text{cont}} = \frac{\pi D^2}{4} \cdot 5\% = \frac{\pi D^2}{4} \cdot 0,05 = 0,039 \text{ sq. mm} , \quad (1)$$

in which  $D$  is the beam diameter ( $D = 1$  mm in the case of our example). The total area  $S_0$  of the  $5\text{-}\mu\text{m}$  width ( $b = 5\text{ }\mu\text{m}$ ) metal contacts enclosed within the circle  $D = 1$  mm is:

$$S_0 \approx 2 \cdot D \cdot b = 2 \cdot 1 \cdot 0.005 = 0.01 \text{ sq. mm} \quad (2)$$

From equations 1 and 2, it is clear that  $S_0 < S_{\text{cont}}$ ; therefore,  $5\text{-}\mu\text{m}$  width contact runs on the die back side satisfy the optimization requirements of securing a good electrical contact and high total reflectance of the back surface of the die.

If for the given structure the requirement  $S_0 \leq S_{\text{cont}}$  does not hold, then the values of  $a$  and  $b$  (see Figures 3 and 4) preferably should be changed to keep the ratio  $a/b$  within optimal limits.

An exemplary method of fabricating a structure that satisfies the requirements of a high back surface optical reflectance and excellent electrical performance of the photodiode die comprises:

- a) A part of the front surface and back surface processing may be standard and is not the object of this invention. It may include, but may not be limited to:
  - Guard ring/channel stopper deposition, drive, and oxidation - if required (not shown);
  - Back side contact doping - second electrode - enhancement & oxidation;
  - Front side first electrode dopant deposition, drive and oxidation;
  - Front side contact opening;

- Front and back side metal deposition and sintering.
- b) The following steps are the objects of this invention:
  - The back side oxide layer grown during initial steps of wafer processing is not removed;
  - The additional photo process is applied to open contacts in the oxide layer on the back side. This photo process could either precede the front side contact openings or may immediately follow it. The mask design should be in accord with the considerations given above in the description of the first embodiment of the invention.

Figure 5 presents a cross section of an exemplary photodiode in accordance with the present invention. The topside of the photodiodes may be in accordance with the prior art, having a protective oxide layer 6 with a patterned metal layer 7 thereover making contact with the first electrode. The back side incorporates the increased reflectivity over the majority of the back side, yet preserves the desired good electrical contact characteristics, and can be designed to provide a desired uniformity of responsivity over the photodiode area.

Thus, the present invention provides a design for silicon photodiodes and photodiode back side structures that provides high quantum efficiency of the photodiode within the spectral range close to the bandgap, and provides superior temporal characteristics. The present invention also provides related fabrication methods for the photodiodes and photodiode back side structures. The highly reflective back surface structure for silicon photodiodes also greatly



improves the photodiode temporal characteristics and, therefore, is useful in construction of fast photodiodes in near infrared spectral range.

CLAIMS

What is claimed is:

1. A photodiode comprising:
  - a silicon substrate of a first conductivity type having first and second surfaces;
  - a region of a second conductivity type on the first surface of the substrate;
  - a region of a first conductivity type on the second surface of the substrate, the region of a first conductivity type on the second surface of the substrate having a higher conductivity than the substrate;
  - a patterned isolation layer on the region of a first conductivity type on the second surface of the substrate;
  - and,
  - a metal layer on the patterned isolation layer and contacting the region of a first conductivity type on the second surface of the substrate between regions of the patterned isolation layer.
2. The photodiode of claim 1 wherein pattern of the patterned isolation layer is a repetitive pattern.
3. The photodiode of claim 2 wherein the isolation layer is an oxide layer.
4. The photodiode of claim 2 wherein the isolation layer is a nitride layer.
5. The photodiode of claim 2 wherein the pattern is a repetitive pattern of rectangular regions.
6. The photodiode of claim 1 wherein the substrate is an n-type substrate.

7. The photodiode of claim 1 wherein the substrate is an p-type substrate.

8. The photodiode of claim 1 further comprised of an oxide layer over the region of a second conductivity type and surrounding substrate, and a patterned metal layer over the oxide layer and making electrical contact with the region of a second conductivity type through an opening in the oxide layer.

9. A method of forming a photodiode comprising:  
providing a silicon substrate of a first conductivity type having first and second surfaces;  
doping the second surface of the substrate to provide a layer of the first conductivity type of higher conductivity than the substrate and providing a layer of oxide thereover;  
doping the first surface of the substrate to provide a layer of the second conductivity type and providing a layer of oxide thereover;

masking and etching the oxide layers on the first and second surfaces of the substrate to expose a contact region to the layer of the second conductivity type and to pattern the oxide layer on the second surface to expose a complementary pattern of the layer of the first conductivity type of higher conductivity than the substrate; and,

providing a layer of metal on the second surface of the substrate and a patterned layer of metal on the first surface of the substrate.




Figure 1




Figure 2




Figure 3




Figure 4




Figure 5



## INTERNATIONAL SEARCH REPORT

Int. Application No.  
PC17U52004/031032

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 H01L31/0232 H01L31/103

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 968 634 A (KUHLMANN WERNER) 6 November 1990 (1990-11-06) abstract	1-9
Y	US 5 026 148 A (SATO ROBERT N ET AL) 25 June 1991 (1991-06-25) figure 5	1-9
A	US 6 423 980 B1 (GUNAPALA SARATH D ET AL) 23 July 2002 (2002-07-23) the whole document	1-9
A	US 4 419 533 A (CZUBATYJ WOŁODYMYR ET AL) 6 December 1983 (1983-12-06) figure f	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*I\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \*A\* document member of the same patent family

Date of the actual completion of the international search

21 December 2004

Date of mailing of the international search report

04/01/2005

Name and mailing address of the ISA  
European Patent Office, P.B. 5816 Patentplan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 51 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Werner, A

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Application No.  
PC/US2004/031032

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4968634 A	06-11-1990	DE 58907059 D1 EP 0342391 A1 JP 2020073 A	07-04-1994 23-11-1989 23-01-1990
US 5026148 A	25-06-1991	NONE	
US 6423980 B1	23-07-2002	AU 5893400 A EP 1192662 A1 WO 0101494 A1	31-01-2001 03-04-2002 04-01-2001
US 4419533 A	06-12-1983	AU 543213 B2 AU 1149483 A BR 8300902 A CA 1187970 A1 DE 3306148 A1 EG 15060 A ES 8403667 A1 FR 2522880 A1 GB 2116364 A ,B GR 78799 A1 IE 54408 B1 IL 67794 A IN 157618 A1 IT 1167617 B JP 58159383 A NL 8300603 A PH 19299 A SE 454225 B SE 8301051 A ZA 8300748 A	04-04-1985 08-09-1983 16-11-1983 28-05-1985 15-09-1983 31-12-1985 16-06-1984 09-09-1983 21-09-1983 02-10-1984 27-09-1989 31-01-1986 03-05-1986 13-05-1987 21-09-1983 03-10-1983 05-03-1986 11-04-1988 04-09-1983 30-11-1983